

STEELS STOCK

CARBON STEELS

UNI	EN	AFNOR	DIN	ASTM/SAE/AISI	Wr.
C20	1C22 / 2C22 / 3C24	XC18		1020	
C25	1C25 / 2C25 / 3C25	XC25	CK22	1025	
C30	1C30 / 2C30 / 3C30	XC32	CK35	1030	1.1178
C40	1C40 / 2C40 / 3C40	XC38		1040	1.1186
C45	1C45 / 2C45 / 3C45	XC42	CK45	1045	1.1191
C50	1C50 / 2C50 / 3C50	XC48		1050	1.1206
Fe 510B	S355JR	E36.2	St 50.2	A 105	
Fe 510D	S355J2G3	E36.3	St 52.3	A350 LF2	
Fe 360B	S235JR	E24.2	St37.2		
Fe 360C	S235JO	E24.3	St 37.3U		
Fe 360D	S275J2G3	E28.4	St 44.3N		
Fe 430B	S275JR	E28.2	St 44.2		
				A694 F52	
				A694 F60	
				A694 F65	

ALLOY STEELS

UNI	EN	AFNOR	DIN	ASTM/SAE/AISI	Wr.
18NiCrMo5	17NiCrMo6.4	18NCD6		4317	1.6566
		16NC6			1.5919
16NiCrMo12	14NiCrMo13.4	16NCD13			1.6657
18CrNiMo7.6	18CrNiMo7.6	18NCD6	17CrNiMo6	4320	1.6587
25CrMo4	25CrMo4	25CD4	25CrMo4	4125	1.7218
30CrMo4		30CD4	30CrMo4	4130	1.7219
35CrMo4	34CrMo4	35CD4	34CrMo4	4135	1.7220
42CrMo4	42CrMo4	42CD4	42CrMo4	4140	1.7225
39NiCrMo3	36NiCrMo4	40NCD3			1.6511
				8630	
	34CrNiMo6		34CrNiMo6		1.6582
40NiCrMo7				4340	1.6562
30NiCrMo8	30CrNiMo8	30CND8	30NiCrMo8		1.6580
27NiCrMoV11.6	27NiCrMoV11.6				1.6948
30NiCrMoV12		30NCD12	32NiCrMo10.4		1.6655
31CrMoV10	30CrMoV9		30CrMoV9		1.7707
36NiCrMo16	36NiCrMo16	35NCD16	36NiCrMo16.6		1.6773
41CrAlMo7		40CAD6.12	41CrAlMo7		1.8507
32CrMo12	32CrMo12		32CrMo12		1.7361
18CrMoSi4 KW		10CD6		A182 F11	1.7338
14CrMo3		15CD4.05	13CrMo4.4	A182 F12	1.7335
12CrMo9.10		10CD9.10	10CrMo9.10	A182 F22	1.7380
	X10CrMoVNb9.1				

STEELS STOCK

STAINLESS STEELS

UNI	EN	AFNOR	DIN	ASTM/SAE/AISI	Wr.
X5CrNiMo17.12	X5CrNiMo17.12.2	Z6CND17.11	X5CrNiMo18.10	A182 F316	1.4401
X2CrNiMo17.12	X2CrNiMo17.12.2	Z2CND17.12	X2CrNiMo18.10	A182 F316L	1.4404
X12Cr13	X12Cr13	Z12C13	X15Cr13	410-A182 F6a	1.4006
	X3CrNiMo13.4		X5CrNi13.4	A182 F6NM	1.4313
X4CrNiMo16.5.1	X4CrNiMo16.5.1				1.4418
X5CrNi18.10	X5CrNi18.10			A182 F304	1.4301
X2CrNi18.9	X2CrNi18.9			A182 F304L	1.4307
	X1CrMoCuN20.18.7		X1CrMoCuN20.18.7	A182 F44	1.4547
	X5CrNiCuNb16.4	Z6CNU17.04	X5CrNiCuNb17.4	A 630 17.4PH	1.4542

DUPLEX and SUPERDUPEX STEELS

UNI	EN	AFNOR	DIN	ASTM/SAE/AISI	Wr.
	X2CrNiMoN22.5.3	Z2CND22.05 AZ	X2CrNiMoN22.5.3	A182 F51	1.4462
	X2CrNiMoN25.7.4	Z3CND25.07 AZ	X2CrNiMoN25.7.4	A182 F53	1.4410
	X2CrNiMoCuWN25.7.4	Z3CND25.06 AZ	X2CrNiMoCuWN25.7.4	A182 F55	1.4501

TOOL STEELS

UNI	ISO 4957	ANFNOR	DIN	AISI	Wr.
35CrMo8KU		40CMD8	40CrMnMo7	P20	1.2311
		40CMD8+S	40CrMnMoS8		1.2312
			46CrSiMoV7		1.2329
X37CrMoV51KU	X37CrMoV5-1	Z38CDV5	X38CrMoV51	H11	1.2343
X40CrMoV511KU	X40CrMoV5-1	Z40CDV51	X40CrMoV51	H13	1.2344
56NiCrMoV7KU	55NiCrMV7	55NCDV7	56NiCrMoV7	6F3	1.2714
	40CrMnNiMo8-6-4	40CMND8	40CrMnNiMo8	P20+Ni	1.2738
	X38CrMoV5-3	Z38CDV5-3			1.2367

NICHEL ALLOYS

Commercial Grade	USA UNS	Wr.
Alloy 800H	N08810	
Alloy 800HT	N08811	
Alloy 800	N08800	1.4876
Alloy 825	N08825	2.4858
Alloy 625	N06625	2.4856
Alloy 718	N07718	2.4668
Alloy 725	N07725	